



SUMIKASUPER E6808UHF Z

		Method	Unit	E6808UHF Z
Color				Natural, Black
Filler		-		Glass fiber/Mineral
Glass fiber type		-		Milled
Filler content		-	%	40
Physical property				
Specific gravity		ASTM D792		1.72
Mold shrinkage	MD	Sumitomo Original ^{*1}	%	0.22
	TD		%	1.02
Mechanical property				
Tensile	strength	ASTM D638	MPa	100
	elongation		%	5.0
	strength	ISO 527	MPa	78
	modulus		GPa	-
	elongation		%	2.8
Flexural	strength	ASTM D790	MPa	120
	modules		GPa	9.4
	strength	ISO 178	MPa	110
	modulus		GPa	8.9
Izod impact strength		D256	J/m	350
Non-notched		ISO 180	J/m	311
Charpy impact strength		ISO 179	KJ/m ²	-
Non-notched			KJ/m ²	45
Rockwell strength			R scale	96
Thermal property				
TDUL		ASTM D648	deg C	240
1.82MPa for ASTM/1.80MPa for ISO		ISO 75	deg C	228
Solder resistance		Sumitomo Original ^{*2}	deg C	290
Liner expansion coefficient	MD	Sumitomo Original ^{*3}	×10 ⁻⁵ /deg C	1.0
	TD			6.2
Electrical property				
Dielectric constant		ASTM D150	1MHz	3.8
			1GHz	3.4
Dielectric tangent			1MHz	0.033
			1GHz	0.004
Dielectric breakdown voltage		Short time method	kV/mm	-
Specific volume resistance		ASTM D257	Ωm	10 ¹³
Specific surface resistance			Ω	-

Arc resistance	ASTM D495	sec.	132
Tracking resistance	IEC method	V	200
Flammability			
Flame retardency	UL 94		V-0 at 0.3mmt
Limited Oxygen Index	JIS K 7201		48

<Note>

All the data above are just for reference, not intended for any guarantee on the product.

*1: The tool of 64mm X 64mm X 3mmt was used to determine mold shrinkages.

*2: The highest temperature at which dumbbell shaped test pieces of 1.2mmt does not deform after immersing in a solder bath for 60 seconds.

*3: The center part of the test piece for tensile property was used.

Standard molding conditions			
Pre-drying		deg C for hours	About 130 deg C for 4 to 24 hours
Cylinder temperature	Nozzle	deg C	340 to 360
	Front	deg C	340 to 360
	Middle	deg C	320 to 340
	Rear	deg C	280 to 320
Suitable resin temperature		deg C	350
Tool (Mold) temperature		deg C	40 to 160
Injection velocity		-	Middle to High
Injection pressure		MPa	80 to 160
Holding pressure		MPa	20 to 40
Back pressure		MPa	1 to 5
Screw rotation		rpm	50 to 100